

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 September 2005 (29.09.2005)

PCT

(10) International Publication Number
WO 2005/090498 A1

(51) International Patent Classification⁷: **C09D 11/02**,
B41M 1/06

(21) International Application Number:
PCT/US2005/008504

(22) International Filing Date: 14 March 2005 (14.03.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0405658.6 12 March 2004 (12.03.2004) GB

(71) Applicant (for all designated States except US): **SUN
CHEMICAL CORPORATION** [US/US]; 35 Waterview
Boulevard, Parsippany, NJ 07054 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **PULINA, Tillman**
[DE/DE]; Im Munchsgraben 11, 61130 Nidderau-Helden-
bergen (DE). **FALKENBERG, Wolfram** [DE/DE];
Buchenweg 7, D-61118 Bad Villbel (DE).

(74) Agent: **PERSLEY, Sidney**; 35 Waterview Boulevard, Par-
sippany, NJ 07054 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ,
TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA,
ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: LOW MIGRATION, LOW ODOUR OFFSET INKS OR VARNISHES

(57) Abstract: An offset printing ink or varnish uses as a solvent at least one water-insoluble ester of a polycarboxylic acid with an alcohol having at least 4 carbon atoms.



WO 2005/090498 A1

LOW MIGRATION, LOW ODOUR OFFSET INKS OR VARNISHES

The present invention relates to novel low migration, low odour inks useful for offset
5 lithographic printing, especially sheetfed offset lithographic printing.

Sheetfed offset lithography is the dominant printing process for the printing of folding
cartons for many purposes, including for use as food packaging. However, where an ink is to be
used on food packaging, it is essential, from the point of view of customer acceptance, that it
should not contaminate the food or impart any unnatural odour to it. Moreover, there is an
10 increasing tendency for legislation to prescribe very low levels of contaminants in foods and
other matter which could affect public health. Contamination, in this context, can result from
migration of components of an ink into the foodstuff or other packaged material or from
undesirable odours imparted to the packaged material by the ink.

There is, therefore, a need for a printing ink which can be used for sheetfed offset
15 lithography and which allows little or no migration of its components whilst being essentially
odourless or having little odour. The nature of the offset lithography process also implies severe
restrictions on the ink formulation, as explained in *The Printing Ink Manual* by R.H. Leach *et al.*
[Fifth edition (1993) pages 342-346], and meeting all of these requirements is not an easy task.

One of the main odorous components of offset inks is the solvent used. It is in the nature
20 of offset lithography that the solvent must be organic and insoluble in water. Many solvents
having these properties are not only highly odorous but also many of them are toxic to a greater
or lesser extent. The choice of solvents for this purpose is, therefore, highly restricted.

US Patent No. 6,613,813 attempts to overcome these problems by the use, *inter alia*, of a
solvent comprising an ester of a multivalent alcohol with a fatty acid. The composition can
25 optionally contain a multifunctional allyl ester of a multivalent organic acid; however, the
function of these esters is to enhance the drying process by undergoing oxidative drying, rather
than to serve as a substantial part of the solvent system. Whilst the solution proposed in US
Patent No. 6,613,813 is effective, the Examples of the patent seem to suggest that an additional
drying agent is necessary to achieve the required drying in a reasonable time.

30 We have now discovered that a class of compounds based on polycarboxylic acids are
useful as solvents for offset printing inks and are capable giving a number of improvements over

the known inks of US Patent No. 6,613,813, including equivalent or lower odour, equivalent or lower migration, and equivalent or improved stability on the press.

Thus, the present invention consists in an offset printing ink or varnish, particularly useful in sheetfed offset lithographic printing, characterised in that the solvent comprises at least one water-insoluble ester of a polycarboxylic acid with a monohydric alcohol having at least 4 carbon atoms.

As the oxidative drying process and the by-products generated by it are an important source of odour development in finished prints, a careful selection of raw materials is necessary. Driers as well as raw materials with oxidative drying potential as used in conventional sheetfed offset inks should preferably be excluded. Good rub resistance of the print job may be achieved by using the inks of the present invention in combination with a water based overprint varnish (OVP).

The composition of printing inks or varnishes for offset lithographic printing, including sheetfed offset lithographic printing, is very well known, and is described in considerable detail in, for example, *The Printing Ink Manual (supra)* pages 342-452, and in US Patents No 5,382,282, No. 5,725,646 and No. 6,489,375.

In general terms, a lithographic printing ink should have a low surface tension, be water-repellent, be capable of emulsifying with a fountain solution, and, for conventional sheetfed offset lithography, must be capable of drying without radiation. These very particular requirements are met by careful formulation and choice of the various components and is well known in the printing ink industry.

The solvent used in the ink or varnish composition of the present invention is a water-insoluble ester of a polycarboxylic acid with an alcohol having at least 4 carbon atoms. The polycarboxylic acid may be aromatic or aliphatic, although it is preferably aromatic, and should have more than one carboxylic acid group. Preferably, the acid has from 2 to 4, more preferably 3, carboxylic acid groups.

Examples of aromatic polycarboxylic acids include: trimellitic acid, phthalic acid, isophthalic acid, terephthalic acid, 1,2,3-benzenetricarboxylic acid, 1,2,4-benzenetricarboxylic acid, 1,3,5-benzenetricarboxylic acid, 1,2,3,4-benzenetetracarboxylic acid, 1,2,3,5-benzenetetracarboxylic acid, 1,2,4,5-benzenetetracarboxylic acid, 1,3,5-naphthalenetetracarboxylic acid, 1,3,6-naphthalenetetracarboxylic acid, 6-carboxy-1-(carboxymethyl)-2-naphthalenepropionic acid,

1,4,5,8-naphthalenetetracarboxylic acid, 3,3',4,4'-biphenyltetracarboxylic acid and 3,4,9,10-perylenetetracarboxylic acid. Of these, trimellitic acid is preferred.

Examples of aliphatic polycarboxylic acids include: dicarboxylic acids, such as oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, tartronic acid, malic acid and tartaric acid; tricarboxylic acids, such as citric acid, acetylcitric acid, 2-hydroxy-2-methylpropane-1,2,3-tricarboxylic acid, pentane-1,3,5-tricarboxylic acid, 1,2,3-propanetricarboxylic acid, and 7-methyl-1,7,9-decanetricarboxylic acid; and tetracarboxylic acids, such as 1,2,3,4-butanetetracarboxylic acid, cyclopentane-1,2,3,4-tetracarboxylic acid, 2,3,4,5-tetracarboxytetrahydrofuran, and 1,1,12,12-dodecanetetracarboxylic acid.

The monohydric alcohol with which these polycarboxylic acids form esters has at least 4 carbon atoms, and preferably from 4 to 20, more preferably from 4 to 18, and still more preferably from 6 to 10, carbon atoms. Examples of such alcohols include: butanol, sec-butanol, t-butanol, pentanol, hexanol, heptanol, octanol, nonanol, decanol, undecanol, dodecanol, tridecanol, tetradecanol, pentadecanol, hexadecanol, heptadecanol, octadecanol, nonadecanol, icosanol, hexan-2-ol, 2,3-dimethylbutan-2-ol, 3-methyl-pentan-1-ol, 3,3-dimethylbutan-2-ol, and 2,3,3-trimethylbutan-2-ol.

A particularly preferred polycarboxylic acid ester solvent in accordance with the present invention is that sold under the trade name Uraplast 525 by DSM Resins bv. This is a low viscosity trialkyl trimellitate based on C₈ – C₁₀ alcohols. It has previously been used as a plasticiser. Other suitable solvents include tridecyl trimellitate, tributyl citrate and acetyl tributyl citrate.

In order that the ester of the polycarboxylic acid and the monohydric alcohol should be able to function as a solvent, it is normally important that its molecular weight be within a specific range. In general, a molecular weight of at least 250, and more preferably at least 300, is preferred, the maximum preferred molecular weight being 1000. Thus, the molecular weight is preferably from 250 to 1000, more preferably from 300 to 1000 and still more preferably from 500 to 800.

Although the polycarboxylic acid ester may be used as the sole solvent in the compositions of the present invention, it may be necessary, in order to achieve the correct rheological properties, to include also another solvent. This other solvent, if present, preferably does not exceed 60% of the total solvent present in the composition. More preferably, from 45%

to 90%, still more preferably from 50% to 80%, and most preferably from 55% to 65%, by weight of said solvent comprises the polycarboxylic acid ester.

If another solvent is present, any solvent conventionally used in lithographic inks may be employed, provided that it has no oxidative drying potential and that it does not tend to migrate from the dried ink. Examples of such other solvents include triglycerides of C₈ – C₂₀ aliphatic carboxylic acids, for example, coconut oil, such as that sold under the trade name Kokosöl by Lechner and Crebert.

The solvent, or mixture of solvents, used in the present invention preferably has a melting point such that it is liquid at the temperature at which the printing ink or varnish is to be used. This normally means that it should be liquid at the temperature of the printing press, and preferably at ambient temperature, e.g. at temperatures above 10-15°C. In some cases, however, for example if the printing ink or varnish is to be used only in a warm atmosphere, it may be possible that the solvent is solid at these temperatures, provided that it melts at a somewhat higher temperature, for example about 25°C.

The resin component in a lithographic ink composition or varnish functions, among other things, as a film former to bind the varnish and pigment together and, when the ink or varnish dries, to bind the same to the receiving substrate. The resin component also contributes to the properties of hardness, gloss, adhesion and flexibility of an ink and must be compatible with the solvent component of the varnish. In conventional oleoresinous systems, the resin component commonly comprises a first or hard resin component and a second resin component which typically is an alkyd or polyester resin, but which can comprise various other compositions and resins as well.

Hard resins usable in the lithographic inks or varnishes of the present invention include, for example, natural or processed resins such as rosins, rosin esters, maleic modified resins, rosin modified fumaric resins, dimerised and polymerised rosins, , phenolics, rosin modified phenolics, terpenes, polyamides, cyclised rubber, acrylics, hydrocarbons and modified hydrocarbons. Also included among the available resins are those identified in *The Printing Ink Manual*, supra, the substance of which is incorporated herein by reference.

The lithographic inks of the present invention will usually include at least one pigment, the nature of which is not critical to the present invention, and which may be chosen from any of those pigments well known to those skilled in the art. Alternatively, the ink may include an extender. Varnishes will not normally include any pigment or extender in their composition.

In addition, there may, if desired, be present other additives, such as antioxidants, waxes, anti-set-off compounds, lithographic additives and rheology modifiers. These are likewise well known to those skilled in the art.

The invention is further illustrated by the following non-limiting Examples.

5

EXAMPLES 1-4

Preparation of inks

10 The components shown in the following Table 1 were blended as described below to produce inks suitable for use in sheet fed offset lithographic printing.

Table 1

			Example No.			
			1	2	3	4
Name	Supplier	Material	Yellow	Magenta	Cyan	Black
Talkum Finntalk M 05	Omya	Talcum	2.00	1.00	-	-
Aerosil R 972 V	Fischer	Pigment White 27	1.10	1.10	2.10	1.10
Irgalith LB1W	Ciba	Pigment Yellow 13	6.00	-	-	-
Permanent Yellow GRX 86	Clariant	Pigment Yellow 176	6.00	-	-	-
Diacetanil Orange R 3426C	Capelle	Pigment Orange 34	0.04	-	-	-
Symuler Brilliant Carmin 6B 308	DIC	Pigment Red 57:1	-	8.00	-	1.00
Symuler Brilliant Carmin 6B 303	DIC	Pigment Red 57:1	-	8.00	-	-
Fastogen Blue H 5375 SD	DIC	Pigment Blue 15:3	-	-	16.00	4.00
Russ Elftex 415	Cabot	Pigment Black 7	-	-	-	8.50
Russ Printex 25	Degussa	Pigment Black 7	-	-	-	8.50
Tergraf ND 2030	Cray Valley	Phenolic modified rosin ester	13.40	12.70	13.00	11.80
Tergraf 902	Cray Valley	Phenolic modified rosin ester	13.40	12.70	13.00	11.80
Uraplast 525	DSM	Trialkyl trimellitate	31.40	31.10	29.70	29.50
Coconut oil	Lechner & Crebert	Coconut oil refined	24.75	23.52	24.31	21.96
Printwax ME 0520	Deurex	Polyethylene	1.20	1.20	1.20	1.20
Additol VXL 12	Surface	Aluminium gelling	0.61	0.58	0.59	0.54

	Chemie	agent				
MTBHQ	Eastman	t-butylhydroquinone	0.10	0.10	0.10	0.10
Total			100.00	100.00	100.00	100.00

The coconut oil and approximately one half of the Uraplast 525 were added to a reaction vessel, stirred and heated to 180°C. Tergraf ND 2030 and Tergraf 902 were then added, ensuring that the temperature did not fall below 160°C. The mixture was heated up to 180°C and held at that temperature for 60 minutes. Approximately another one half of the total amount of the Uraplast 525 was then added and the mixture was allowed to cool to 160°C. The gelling agent was then added with quick stirring, and the whole varnish was heated to 180°C and maintained at that temperature for 30 minutes. External cooling then reduced the temperature to 110°C, and the varnish was discharged from the reaction vessel.

The pigment(s) and other solid components (except the polyethylene wax) were dispersed in the varnish and the mixture was thoroughly mixed with a triple roller mill. The polyethylene wax was then added and the mixture was again passed over the triple roller mill for de-airing. The viscosity and tack were adjusted, prior to de-airing, by addition of small amounts of the trialkyl trimellitate, to give the final composition shown in Table 1.

EXAMPLE 5

Preparation of ink

The following components were mixed to form a magenta ink, following essentially the same procedure as described in Examples 1-4. The amounts are parts by weight.

Name	Supplier	Material	Amount
Citrofol B1	Jungbunzlauer	Tributyl citrate	23.10
Beckosol HS 201-100	Reichhold	Unsaturated polyester	10.00
		Sodium aluminium silicate	0.80
Talkum Finntalk M 05	Omya	Talc	1.00
Symuler Brilliant Carmine	DIC	PR 57:1	16.50
Coconut oil	Lechner & Crebert	Coconut oil refined	23.50
Krumbhaar LR 10040	Eastman	Phenolic modified rosin ester	8.20
Tergraf 902	Cray Valley	Phenolic modified rosin ester	16.40
Additol VXL 12	Surface Chemie	Aluminium gelling agent	0.50
			100.00

EXAMPLE 6

Preparation of ink

- 5 The following components were mixed to form a magenta ink, following essentially the same procedure as described in Examples 1-4. The amounts are parts by weight.

Name	Supplier	Material	Amount
Citrofol BII	Jungbunzlauer	Acetyltributyl citrate	17.90
Citrofol BI	Jungbunzlauer	Tributyl citrate	4.20
Foralyn 5020 F	Eastman	Hydrogenated resin	10.00
		Sodium aluminium silicate	0.80
Talkum Finntalk M 05	Omya	Talc	1.00
Symuler Brilliant Carmine6B 305	DIC	PR 57:1	16.50
Coconut oil	Lechner & Crebert	Coconut oil refined	24.50
Krumbhaar LR 10040	Eastman	Phenolic modified rosin ester	11.50
Tergraf 902	Cray Valley	Phenolic modified rosin ester	13.10
Additol VXL 12	Surface Chemie	Aluminium gelling agent	0.50
			100.00

EXAMPLE 7**Preparation of ink**

- 5 The following components were mixed to form a magenta ink, following essentially the same procedure as described in Examples 1-4. The amounts are parts by weight.

Name	Supplier	Material	Amount
Citrofol B1	Jungbunzlauer	Tributyl citrate	20.90
Uraplast 525	DSM	Trialkyl mellitate	10.00
		Sodium aluminium silicate	0.80
Talkum Finntalk M 05	Omya	Talc	1.00
Symuler Brilliant Carmine 6B 306	DIC	PR 57:1	16.50
Coconut oil	Lechner & Crebert	Coconut oil refined	25.00
Krumbhaar LR 10040	Eastman	Phenolic modified rosin ester	8.40
Tergraf 902	Cray Valley	Phenolic modified rosin ester	16.90
Additol VXL 12	Surface Chemie	Aluminium gelling agent	0.50
			100.00

EXAMPLE 8**Preparation of ink**

The following components were mixed to form a magenta ink, following essentially the
5 same procedure as described in Examples 1-4. The amounts are parts by weight.

Name	Supplier	Material	Amount
Citrofol B1	Jungbunzlauer	Tributyl citrate	8.00
Uraplast 525	DSM	Trialkyl mellitate	49.00
		Sodium aluminium silicate	0.80
Talkum Finntalk M 05	Omya	Talc	1.00
Symuler Brilliant Carmine 6B 306	DIC	PR 57:1	16.50
Krumbhaar LR 10040	Eastman	Phenolic modified rosin ester	11.30
Tergraf 902	Cray Valley	Phenolic modified rosin ester	12.90
Additol VXL 12	Surface Chemie	Aluminium gelling agent	0.50
			100.00

EXAMPLE 9**Preparation of varnish**

- 5 The following components were mixed to form a varnish, following essentially the same procedure as described in Examples 1-4. The amounts are parts by weight.

Name	Supplier	Material	Amount
Coconut oil	Lechner & Crebert	Coconut oil refined	27.00
Liponate TDTM	Lipo Chemical Inc.	Tridecyl mellitate	24.90
MTBHQ	Eastman	t-butylhydroquinone	0.10
Tergraf ND 2030	Cray Valley	Phenolic modified rosin ester	16.00
Tergraf 902	Cray Valley	Phenolic modified rosin ester	16.00
Liponate TDTM	Lipo Chemical Inc.	Tridecyl mellitate	14.00
Additol VXL 12	Surface Chemie	Aluminium gelling agent	2.00
			100.00

10

EXAMPLES 10-13**Preparation of ink**

- 15 The components listed in Table 2 were mixed to form inks, following essentially the same procedure as described in Examples 1-4. The amounts are parts by weight.

Table 2

			Example No.			
			10	11	12	13
Name	Supplier	Material	Yellow	Magenta	Cyan	Black
Talkum Finntalk M 05	Omya	Talcum	2.00	2.00	3.00	-
Sunbrite Yellow M 05	Sun Chemical	Pigment Yellow 13	12.00	-	-	-
Diacetanil Orange R 3426C	Capelle	Pigment Orange 34	0.04	-	-	-
Symuler Brilliant Carmin 6B 308	DIC	Pigment Red 57:1	-	8.00	-	1.00
Symuler Brilliant Carmin 6B 303	DIC	Pigment Red 57:1	-	8.00	-	-
Fastogen Blue H 5375 SD	DIC	Pigment Blue 15:3	-	-	16.00	4.00
Specialblack 250	Degussa	Pigment Black 7	-	-	-	20.00
Tergraf ND 2030	Cray Valley	Phenolic modified rosin ester	11.57	11.39	11.20	10.35
Tergraf 902	Cray Valley	Phenolic modified rosin ester	11.57	11.39	11.20	10.35
Liponate TDTM	Lipo Chemical Inc.	Tridecyl trimellitate	39.16	36.88	36.37	33.72
Coconut oil	Lechner & Crebert	Coconut oil refined	21.00	19.70	19.60	18.00
Printwax ME 0520	Deurex	Polyethylene	1.20	1.20	1.20	1.20
Additol VXL 12	Surface Chemie	Aluminium gelling agent	0.59	0.57	0.56	0.52
MTBHQ	Eastman	t-butylhydroquinone	0.07	0.07	0.07	0.06
Zeolite Powder 4A	Fischer	Sodium aluminium silicate	0.80	0.80	0.80	0.80

Total			100.00	100.00	100.00	100.00
-------	--	--	--------	--------	--------	--------

EXAMPLE 14

Preparation of printed material

Test prints were produced on a Heidelberg MO 4-colour press including a unit for application of water-based overprint varnishes. Press speed was between 7000-9000 sheets/hour, using a fountain solution containing 6-9% by volume isopropanol. Printing was carried out with standard optical densities, yellow = 1.35, magenta = 1.50, cyan = 1.40 and black = 1.80, using Fuji plates and Astral Premium blankets. The substrate used was Invercote G, which is a standard substrate for packaging. Prints were produced using a water-based overprint varnish. Rub tests were done after 24 hours, and all of the printing inks of the present invention gave satisfactory results.

EXAMPLE 15

Robinson test

The odour and taint caused by the inks of the present invention were tested by the well known Robinson test.

This is a test originally devised by the Technical Committee of the International Office of Cocoa and Chocolate to determine whether odours from packaging materials are transferred to cocoa and chocolate products. It is now also used more generally to check on the odour and taint likely to transfer from packaging materials used in the food industry. The test was carried out as follows:

A petri dish containing about 25 g of fresh grated milk chocolate was placed in a clean 1 litre preserving jar. 16 representative round samples (9 cm diameter, total area of the 16 samples 1017 cm²) of the packaging material to be evaluated were placed in the jar, so that sample and chocolate were not in contact with one another. A jar, the "blank", in all respects similar, but without any sample and a jar with unprinted substrate, were also prepared. The jars were closed

with a lid. They were then stored for 24 hours in a dark, odourless place at 23°C. A panel of tasters then compared the odour and then the flavour of the chocolate in each sample jar with the chocolate in the blank. The results were evaluated on the following scale:

- 0 = No difference in odour/flavour
- 1 = Odour/Flavour difference just perceptible
- 2 = Noticeable change in odour/flavour
- 3 = Significant change in odour/flavour
- 4 = Intense change in odour/flavour

Four-colour (Black, Cyan, Magenta, Yellow) prints were produced by printing as described in Example 14, and were then tested. The sets of inks used were: Set A, standard offset inks, Irocart Process Inks, a set of currently available Sun Chemical conventional sheetfed offset inks containing driers; Set B, Irocart GN Low Hex ink, a set of currently available Sun Chemical conventional sheetfed offset inks formulated for low odour and low taint; Set C, the inks of Examples 1-4; and Set D, the ink of Example 7, and black, cyan and yellow inks prepared in the same way as that of Example 7. The results are shown in Table 3 below.

Table 3

Sample	Odour rating	Taint rating
Blank	0	0
Blank substrate	0.5	0
Set A	3.5	3.0
Set B	0.5	0.5
Set C	0.5	0.5
Set D	1.5	0.5
Ink from US 6,613,813	1.5	1.0
Reference/blank	0	0

It can be seen from these results that the compositions of the present invention (Examples 1 and 7) gave printed matter having comparable or better odour and comparable or lesser taint than the product of US 6,613,813.

EXAMPLE 16**Migration test**

Prints were prepared as described in Example 14 using the inks of Examples 1-4, or - for inks of Example 8 - using a standard Prüfbau laboratory proofing press.

In all cases, the prints were individually placed in a petri dish, and 1 g of clean Tenax® (an absorbent used to simulate dry and/or fatty foods; available from Akzo Nobel) was placed on the reverse of each print. After 10 days at 40°C, the Tenax® was extracted into diethyl ether and analysed using GC-MS (Gas Chromatography - Mass Spectrometry). The materials analysed for were Uraplast 525, Citrofol BI, coconut oil and the solvent used in US Patent No. 6,613,813, of which one trade name is Radia 7187. None was found within the detection limits of the analysis.

The invention has been described in terms of preferred embodiments thereof, but is more broadly applicable as will be understood by those skilled in the art. The scope of the invention is only limited by the following claims.

CLAIMS:

1. An offset printing ink or varnish characterised in that the solvent comprises at least one water-insoluble ester of a polycarboxylic acid with an alcohol having at least 4 carbon atoms.
2. An offset printing ink or varnish according to Claim 1, in which from 45% to 90% by weight of said solvent comprises an ester of a polycarboxylic acid with an alcohol having at least 4 carbon atoms.
3. An offset printing ink or varnish according to Claim 2, in which from 50% to 80% by weight of said solvent comprises an ester of a polycarboxylic acid with an alcohol having at least 4 carbon atoms.
4. An offset printing ink or varnish according to Claim 2, in which from 55% to 65% by weight of said solvent comprises an ester of a polycarboxylic acid with an alcohol having at least 4 carbon atoms.
5. An offset printing ink or varnish according to any one of the preceding Claims, in which said alcohol has from 4 to 20 carbon atoms.
6. An offset printing ink or varnish according to Claim 5, in which said alcohol has from 6 to 10 carbon atoms.
7. An offset printing ink or varnish according to any one of the preceding Claims, in which said polycarboxylic acid has from 2 to 4 carboxylic acid groups.
8. An offset printing ink or varnish according to Claim 7, in which said polycarboxylic acid has 3 or 4 carboxylic acid groups.
9. An offset printing ink or varnish according to any one of the preceding Claims, in which said polycarboxylic acid is an aromatic polycarboxylic acid.
10. An offset printing ink or varnish according to Claim 9, in which said polycarboxylic acid is a benzenepolycarboxylic acid.
11. An offset printing ink or varnish according to Claim 10, in which said benzenepolycarboxylic acid is trimellitic acid.

12. An offset printing ink or varnish according to Claim 11, in which the ester is an ester of trimellitic acid with one or more straight chain saturated C₈ – C₁₀ aliphatic alcohols.
13. An offset printing ink or varnish according to Claim 11, in which the ester is tridecyl trimellitate.
14. An offset printing ink or varnish according to Claim 11, in which the ester is an ester of citric acid or acetylcitric acid.
15. An offset printing ink or varnish according to Claim 14, in which said ester is the butyl ester.
16. An offset printing ink or varnish according to any one of the preceding Claims, in which said solvent additionally comprises at least one triglyceride of C₈ – C₂₀ aliphatic carboxylic acids.
17. An offset printing ink or varnish according to Claim 16, in which said triglyceride is a triglyceride of C₁₀ – C₁₈ aliphatic carboxylic acids.
18. An offset printing ink or varnish according to Claim 17, in which said triglyceride is coconut oil.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US2005/008504

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09D11/02 B41M1/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C09D B41M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 2002, no. 08, 5 August 2002 (2002-08-05) & JP 2002 121452 A (SAKATA CORP), 23 April 2002 (2002-04-23) abstract	1-7
X	US 5 965 633 A (REVOL ET AL) 12 October 1999 (1999-10-12) column 4, lines 4,5; claim 1	1,5-7
A	US 6 613 813 B1 (BORGMANN URSULA ET AL) 2 September 2003 (2003-09-02) cited in the application column 1, lines 3-8; claims 1-10 column 1, line 42 - column 3, line 13	1-18

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

2 June 2005

Date of mailing of the international search report

09/06/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dury, O

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2005/008504

Box II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: —
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box II.2

Claims Nos.: -

Present claims 1-18 relate to solvent which are esters of a polycarboxylic acid with an alcohol (generic term). Support within the meaning of Article 6 PCT and/or disclosure within the meaning of Article 5 PCT is to be found, however, for only esters of polycarboxylic acid with monoalcohols (see page 3, lines 11-17).

In the present case, the claims so lack support, and the application so lacks disclosure, that the search has been carried out for those parts of the claims which appear to be supported and disclosed, namely those parts relating to esters of a polycarboxylic acid with a monohydric alcohol.

Besides, the term "water insoluble" is vague and is considered as a non limiting feature.

The applicant's attention is drawn to the fact that claims relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure. If the application proceeds into the regional phase before the EPO, the applicant is reminded that a search may be carried out during examination before the EPO (see EPO Guideline C-VI, 8.5), should the problems which led to the Article 17(2) declaration be overcome.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2005/008504

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 2002121452	A	23-04-2002	NONE	
US 5965633	A	12-10-1999	AT 177464 T	15-03-1999
			AU 5512596 A	21-11-1996
			DE 69601706 D1	15-04-1999
			DE 69601706 T2	14-10-1999
			DK 823931 T3	27-09-1999
			EP 0823931 A1	18-02-1998
			ES 2130815 T3	01-07-1999
			WO 9634923 A1	07-11-1996
			JP 11505556 T	21-05-1999
			NO 975059 A	03-11-1997
US 6613813	B1	02-09-2003	DE 19653828 A1	25-06-1998
			AT 199736 T	15-03-2001
			CA 2245178 A1	02-07-1998
			WO 9828373 A1	02-07-1998
			DE 59703142 D1	19-04-2001
			DK 886671 T3	23-07-2001
			EP 0886671 A1	30-12-1998
			ES 2155706 T3	16-05-2001